

Technical Data Sheet

Revision Date: 2017-06-09
Name: WANNATE[®] HT-75B

NO. PCS_0011
Version: 3.0

Application

WANNATE[®] HT-75B (solution of 1,6-hexamethylene diisocyanate based polyisocyanate) is an aliphatic polyisocyanate based on hexamethylene diisocyanate (HDI) and dissolved in of 25% n-butyl acetate, colorless to slightly yellowish clear liquid.

Equivalent Weight ~ 256

Density at 25 °C ~ 1.08 g/cm³

WANNATE[®] HT-75B can be used as the hardener component for lightfast two-component polyurethane coatings with high resistance to chemicals and weathering, very good gloss retention and outstanding mechanical properties.

The main applications for coatings based on WANNATE[®] HT-75B are automotive refinishing, transportation, industrial finishing and plastics.

Specification

Properties	Unit	Specification
NCO Content	%	16.00 ~ 17.00
Solids	%	74.0 ~ 76.0
Viscosity at 25 °C	mPa s	60 ~ 100
Chromatic Number	APHA	≤ 40
HDI Content	%	≤ 0.20

Package(s)

20 kg Metal drum

60 kg Metal drum

220 kg Metal drum

IBC & ISO TANK

Other packaging available according to customer needs

Storage/ Solubility

Storage in original container. Protect from moisture, heat and foreign material.

WANNATE[®] HB-75B is sensitive to moisture. Storage at higher temperatures will result in increasing of color and viscosity.

WANNATE[®] HT-75B can be thinned with esters, ketones and aromatic hydrocarbons such as ethyl acetate, butyl acetate, methoxypropylacetate, acetone, methyl ethyl ketone, methyl isobutyl ketone, cyclohexanone, toluene, xylene, solvent naphtha 100 and mixtures thereof. Generally speaking, it has good compatibility with the solvents listed. However, the solutions formed must be tested for their storage stability. Only PU grade solvents should be used (max.0.05% water, absence of reactive groups such as hydroxyl or amino groups). Aliphatic hydrocarbons are unsuitable as solvents.

WANNATE[®] HT-75B is not recommended to be thinned to a lower solid content. Prolonged storage of a solution with a lower content may result in turbidity and sedimentation, even gelation.

Compatibility

WANNATE[®] HT-75B can be mixed with the following products: aliphatic polyisocyanates, polyester polyols, aromatic polyisocyanates and polyacrylates.

Shelf Life

WANNATE[®] HT-75B is sensitive to moisture and must be stored in tightly sealed container. It can be stored for at least 9 months at temperatures between 0 and 30 °C.

For more information about safety and environment, please refer to our MSDS or contact our customer service center.

Version Information:

Date of first issue: Oct 6, 2014

Date of 1st revise: Feb 19, 2017 Reason for revision: Change of contact information

Date of 2nd revise: June 9, 2017 Reason for revision: Change of company LOGO

For further information please contact us:

Address: Wanhua Chemical Group Co., Ltd.

No.17, Tianshan Rd, YEDA, Yantai, 264006, China

Customer service: Tel: +86 (535)- 8203244 Fax: +86 (535)- 3388222-3244

Web-site: <http://www.whchem.com> E-mail: PCS@whchem.com

The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products.